CERAN HVA





Extreme-pressure water resistant high temperature calcium sulfonate complex grease.

APPLICATIONS

Multi purpose heavy duty water resistant grease. Applications in steel industry

Recommendation

- CERAN HVA is a heavy duty extreme pressure grease, pre-eminently designed for the lubrication of *closed* industrial bearings working under high temperatures and high loads in the steel industry.
- CERAN HVA is also suitable as EP multi purpose grease, in various other industrial
 applications where water is in frequent contact with the grease.
- Always avoid contamination of the grease by dust and/or dirt when applying. Preferably use a pneumatic pump system.

SPECIFICATIONS

ISO 6743-9: L-XBFHB 2DIN 51 502: KP2R -25

ADVANTAGES

True multi purpose
High loads
Water resistant
High temperatures
Anti corrosion
No harmful substances

- Thanks to its very sophisticated formula and performance reserves, CERAN HVA meets the
 most stringent requirements set by industrial bearing manufacturers.
- Excellent thermal and mechanical stability. It regains its original texture after cooling to ambient temperature.
- Remarkable load resistance thanks to its naturally high extreme pressure and anti-wear properties.
- Extraordinary water resistance, no significant loss of consistency is observed even with high amounts of water entering the grease.
- Excellent anti-oxidation and anti-corrosion properties thanks to the very nature of the calcium sulfonates, also in the presence of sea water.
- CERAN HVA does not contain lead, or other heavy metals considered harmful to human health and the environment.

TYPICAL CHARACTERISTICS	METHODS	UNITS	CERAN HVA
Soap/thickener		-	Calcium sulfonate
NLGI grade	ASTM D 217/DIN 51 818	-	2
Color	Visual	-	Brown
Appearance	Visual	-	Smooth/tacky
Operating temperature range		°C	-25 to 180
Penetration at 25°C	ASTM D 217/DIN51 818	0.1 mm	265-295
Four ball weld load	ASTM D 2596	kgf	500
Anti-rust performance SKF- EMCOR	DIN 51 802/IP220/NFT 60-135/ISO 11007	rating	0-0
Dropping point	IP 396/NF T 60 102 C	°C	>300
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/ IP71	mm²/s (cSt)	420

Above characteristics are mean values given as an information.

