

Taulukko 12. Näytteistä mitatut Cobb-arvot.

SC	yläpinta	4 arkkia		SC	alapinta	5 arkkia		
		Kuiva	Märkä	Cobb30		Kuiva	Märkä	Cobb30
1.	4,628	6,712	208,4	1.	5,644	7,759	211,5	
2.	4,722	6,986	226,4	2.	5,713	8,234	252,1	
3.	4,619	6,271	165,2	3.	5,784	8,086	230,2	
4.	4,576	6,628	205,2	4.	4,766	8,428	366,2	
5.	4,695	6,44	174,5	5.	4,785	8,115	333	
6.	4,706	6,745	203,9	6.	5,832	8,401	256,9	
7.	4,798	7,075	227,7	7.	5,721	8,439	271,8	
8.	4,739	6,98	224,1	8.	5,851	7,504	165,3	
9.	4,741	7,297	255,6	9.	5,82	8,072	225,2	
10.	4,461	6,505	204,4	10.	5,806	8,509	270,3	
11.	4,545	6,698	215,3	11.	5,813	8,39	257,7	
12.	4,524	6,899	237,5	12.	5,572	7,998	242,6	
13.	4,493	6,217	172,4	13.	5,616	7,976	236	
14.	4,492	7,142	265	14.	5,654	7,782	212,8	
15.	4,462	6,948	248,6	15.	5,686	8,228	254,2	
16.	4,387	6,984	259,7	16.	5,778	7,659	188,1	
17.	4,484	6,834	235	17.	5,826	7,934	210,8	
18.	4,454	6,92	246,6	18.	5,754	7,841	208,7	
19.	4,514	6,909	239,5	19.	5,773	8,232	245,9	
20.	4,482	6,791	230,9	20.	5,832	8,166	233,4	
		Keskiarvo	222,3			Keskiarvo	243,6	
LWC	yläpinta	2 arkkia		LWC	alapinta	2 arkkia		
		Kuiva	Märkä	Cobb30		Kuiva	Märkä	Cobb30
1.	2,722	3,314	59,2	1.	2,859	3,448	58,9	
2.	2,727	3,354	62,7	2.	2,763	3,319	55,6	
3.	2,767	3,327	56	3.	2,864	3,432	56,8	
4.	2,751	3,351	60	4.	2,798	3,352	55,4	
5.	2,623	3,248	62,5	5.	2,726	3,316	59	
6.	2,741	3,341	60	6.	2,763	3,299	53,6	
7.	2,767	3,358	59,1	7.	2,712	3,289	57,7	
8.	2,78	3,351	57,1	8.	2,636	3,246	61	
9.	2,723	3,303	58	9.	2,714	3,283	56,9	
10.	2,781	3,378	59,7	10.	2,723	3,303	58	
		Keskiarvo	59,4			Keskiarvo	57,3	

MWC				MWC			
yläpinta				alapinta			
	Kuiva	Märkä	Cobb30		Kuiva	Märkä	Cobb30
1.	2,225	2,562	33,7	1.	2,219	2,569	35
2.	2,257	2,626	36,9	2.	2,257	2,652	39,5
3.	2,244	2,578	33,4	3.	2,237	2,647	41
4.	2,204	2,578	37,4	4.	2,235	2,652	41,7
5.	2,222	2,605	38,3	5.	2,205	2,609	40,4
6.	2,232	2,636	40,4	6.	2,196	2,611	41,5
7.	2,206	2,594	38,8	7.	2,215	2,613	39,8
8.	2,233	2,64	40,7	8.	2,223	2,64	41,7
9.	2,206	2,617	41,1	9.	2,203	2,607	40,4
10.	2,19	2,589	39,9	10.	2,203	2,551	34,8
		Keskiarvo	38,1			Keskiarvo	39,6
WF-pohja				WF-pohja			
yläpinta				alapinta			
	Kuiva	Märkä	Cobb60		Kuiva	Märkä	Cobb60
1.	1,108	1,321	21,3	1.	1,152	1,465	31,3
2.	1,109	1,405	29,6	2.	1,137	1,448	31,1
3.	1,109	1,371	26,2	3.	1,131	1,435	30,4
4.	1,113	1,386	27,3	4.	1,115	1,392	27,7
5.	1,138	1,427	28,9	5.	1,126	1,411	28,5
6.	1,098	1,381	28,3	6.	1,107	1,391	28,4
7.	1,103	1,365	26,2	7.	1,106	1,401	29,5
8.	1,109	1,383	27,4	8.	1,087	1,357	27
9.	1,089	1,36	27,1	9.	1,137	1,419	28,2
10.	1,135	1,412	27,7	10.	1,087	1,375	28,8
		Keskiarvo	27,0			Keskiarvo	29,1
Kopiopaperi				Kopiopaperi			
yläpinta				alapinta			
	Kuiva	Märkä	Cobb60		Kuiva	Märkä	Cobb60
1.	1,539	1,868	32,9	1.	1,544	1,872	32,8
2.	1,514	1,854	34	2.	1,533	1,856	32,3
3.	1,519	1,877	35,8	3.	1,537	1,861	32,4
4.	1,534	1,892	35,8	4.	1,547	1,927	38
5.	1,528	1,883	35,5	5.	1,494	1,834	34
6.	1,534	1,857	32,3	6.	1,53	1,862	33,2
7.	1,538	1,854	31,6	7.	1,542	1,903	36,1
8.	1,516	1,859	34,3	8.	1,524	1,887	36,3
9.	1,535	1,89	35,5	9.	1,528	1,901	37,3
10.	1,519	1,86	34,1	10.	1,521	1,872	35,1
		Keskiarvo	34,2			Keskiarvo	34,8

Pääll. kopiop.				Pääll. kopiop.			
yläpinta				alapinta			
	Kuiva	Märkä	Cobb60		Kuiva	Märkä	Cobb60
1.	1,965	2,311	34,6	1.	1,997	2,313	31,6
2.	1,974	2,312	33,8	2.	1,947	2,245	29,8
3.	1,943	2,272	32,9	3.	1,963	2,271	30,8
4.	1,923	2,251	32,8	4.	1,977	2,282	30,5
5.	1,956	2,281	32,5	5.	1,921	2,23	30,9
6.	1,977	2,3	32,3	6.	1,951	2,292	34,1
7.	1,962	2,299	33,7	7.	1,936	2,246	31
8.	1,954	2,267	31,3	8.	1,907	2,232	32,5
9.	1,948	2,277	32,9	9.	1,94	2,266	32,6
10.	1,98	2,314	33,4	10.	1,916	2,236	32
		Keskiarvo	33,0			Keskiarvo	31,6
							Hylätty
Kirjekuori				Kirjekuori			
yläpinta				alapinta			
	Kuiva	Märkä	Cobb60		Kuiva	Märkä	Cobb60
1.	2,315	2,619	30,4	1.	2,254	2,514	26
2.	2,278	2,585	30,7	2.	2,237	2,496	25,9
3.	2,233	2,533	30	3.	2,223	2,478	25,5
4.	2,263	2,538	27,5	4.	2,242	2,508	26,6
5.	2,269	2,576	30,7	5.	2,265	2,537	27,2
6.	2,284	2,603	31,9	6.	2,244	2,493	24,9
7.	2,294	2,626	33,2	7.	2,253	2,511	25,8
8.	2,235	2,52	28,5	8.	2,181	2,432	25,1
9.	2,257	2,535	27,8	9.	2,253	2,519	26,6
		Keskiarvo	30,1			Keskiarvo	26,0
Release				Release			
yläpinta				alapinta			
	Kuiva	Märkä	Cobb60		Kuiva	Märkä	Cobb60
1.	1,126	1,293	16,7	1.	1,108	1,296	18,8
2.	1,109	1,305	19,6	2.	1,096	1,283	18,7
3.	1,106	1,298	19,2	3.	1,09	1,281	19,1
4.	1,097	1,292	19,5	4.	1,099	1,288	18,9
5.	1,115	1,319	20,4	5.	1,107	1,298	19,1
6.	1,124	1,307	18,3	6.	1,096	1,282	18,6
7.	1,115	1,305	19	7.	1,102	1,297	19,5
8.	1,113	1,318	18,8	8.	1,109	1,316	20,7
9.	1,126	1,306	18	9.	1,115	1,32	20,5
10.	1,123	1,32	19,7	10.	1,116	1,314	19,8
		Keskiarvo	18,9			Keskiarvo	19,4

Tako CX Lite yläpinta				Tako CX Lite alapinta			
	Kuiva	Märkä	Cobb60		Kuiva	Märkä	Cobb60
1.	4,017	4,302	28,5	1.	3,912	4,229	31,7
2.	3,972	4,272	30	2.	3,88	4,209	32,9
3.	3,918	4,22	30,2	3.	3,96	4,308	34,8
4.	3,949	4,26	31,1	4.	3,927	4,264	33,7
5.	3,915	4,217	30,2	5.	3,965	4,282	31,7
6.	3,954	4,268	31,4	6.	3,928	4,265	33,7
7.	3,929	4,226	29,7	7.	4,02	4,381	36,1
8.	3,927	4,269	34,2	8.	3,948	4,267	31,9
9.	3,914	4,226	31,2	9.	3,992	4,366	37,4
10.	3,926	4,244	31,8	10.	3,941	4,298	35,7
		Keskiarvo	30,8			Keskiarvo	34,0
Kemi Brown yläpinta				Kemi Brown alapinta			
	Kuiva	Märkä	Cobb60		Kuiva	Märkä	Cobb60
250g/m2 1.	4,699	5,003	30,4	1.	4,677	5,026	34,9
250g/m2 2.	3,79	4,095	30,5	2.	4,881	5,216	33,5
200g/m2 3.	4,684	4,981	29,7	3.	3,955	4,285	33
200g/m2 4.	3,737	4,046	30,9	4.	4,015	4,337	32,2
250g/m2 5.	4,682	4,985	30,3	5.	4,884	5,285	40,1 Pinnassa vikaa
250g/m2 6.	3,727	4,047	32	6.	4,903	5,329	42,6 Pinnassa vikaa
		Keskiarvo	30,6			Keskiarvo	33,4